

INJECTION FOAM

- ▶ Low Viscosity
- ▶ Rapid Setting
- ▶ Hydrophobic
- ▶ Excellent Adhesion
- ▶ Minimal Shrinkage
- ▶ Maintains Flexibility

*Polyurethane Foam for
Repairing Cracks in Poured
Concrete Foundation Walls*

INJECTION FOAM

- ▶ Low Viscosity
- ▶ Rapid Setting
- ▶ Hydrophobic
- ▶ Excellent Adhesion
- ▶ Minimal Shrinkage
- ▶ Maintains Flexibility

*Polyurethane Foam for
Repairing Cracks in Poured
Concrete Foundation Walls*

INJECTION FOAM

- ▶ Low Viscosity
- ▶ Rapid Setting
- ▶ Hydrophobic
- ▶ Excellent Adhesion
- ▶ Minimal Shrinkage
- ▶ Maintains Flexibility

*Polyurethane Foam for
Repairing Cracks in Poured
Concrete Foundation Walls*

CAUTION

Consult Material Safety Data sheet prior to use. Wear safety glasses and gloves. Avoid contact with skin and eyes

FIRST AID

EYES: Flush with large amounts of water, minimum of 15 minutes.

SKIN: Wash thoroughly with soap and water. Do not apply grease or ointments.

INHALATION: Leave area for fresh air.

INGESTION: Drink 3 to 4 glasses of water. Do not induce vomiting. Seek medical help immediately.

USE ONLY AS DIRECTED

CAUTION

Consult Material Safety Data sheet prior to use. Wear safety glasses and gloves. Avoid contact with skin and eyes

FIRST AID

EYES: Flush with large amounts of water, minimum of 15 minutes.

SKIN: Wash thoroughly with soap and water. Do not apply grease or ointments.

INHALATION: Leave area for fresh air.

INGESTION: Drink 3 to 4 glasses of water. Do not induce vomiting. Seek medical help immediately.

USE ONLY AS DIRECTED

CAUTION

Consult Material Safety Data sheet prior to use. Wear safety glasses and gloves. Avoid contact with skin and eyes

FIRST AID

EYES: Flush with large amounts of water, minimum of 15 minutes.

SKIN: Wash thoroughly with soap and water. Do not apply grease or ointments.

INHALATION: Leave area for fresh air.

INGESTION: Drink 3 to 4 glasses of water. Do not induce vomiting. Seek medical help immediately.

USE ONLY AS DIRECTED

Concrete Sealers USA

P.O. Box 5464 | De Pere, WI 54115

Toll-Free: 888.583.2991 | Fax: 920.759.5100 | Emergency: 800.424.9300
info@concretesealersusa.com | www.concretesealersusa.com

Concrete Sealers USA

P.O. Box 5464 | De Pere, WI 54115

Toll-Free: 888.583.2991 | Fax: 920.759.5100 | Emergency: 800.424.9300
info@concretesealersusa.com | www.concretesealersusa.com

Concrete Sealers USA

P.O. Box 5464 | De Pere, WI 54115

Toll-Free: 888.583.2991 | Fax: 920.759.5100 | Emergency: 800.424.9300
info@concretesealersusa.com | www.concretesealersusa.com

CONCRETESEALERSUSA

Professional Concrete Solutions You Can Trust

Product Description

The CR302 is a high modulus thixotropic epoxy paste designed to seal cracks and adhere surface ports prior to the injection of our CR301 Injection Foam crack repair product. CR302 will cure in the presence of moisture although application onto wet surfaces is not recommended. It is ideal for do-it-yourselfers and inexperienced applicators or contractors due to its extended working time of 6-7 minutes. Allows for injection within 2-3 hours.

CAUTION

Consult Material Safety Data Sheet prior to use. Wear safety glasses and gloves. Avoid contact with skin and eyes.

USE ONLY AS DIRECTED

BATCH # 123456

EPOXY PASTE SURFACE SEALER

Epoxy Paste for Sealing Foundation Wall Cracks & Adhering Surface Ports Prior to Injection

PART A

Parts A and B are mixed
1:1 by volume.

FIRST AID

EYES: Flush with large amounts of water, minimum of 15 minutes. **SKIN:** Wash thoroughly with soap and water. Do not apply grease or ointments. **INHALATION:** Leave area for fresh air. **INGESTION:** Drink 3-4 glasses of water. Do not induce vomiting. Seek medical care immediately.

LIMITED WARRANTY – The Manufacturer warrants products to be free from defects in material or manufacturing. Products are further warranted for adequacy of design when used in accordance with design limits, and properly specified and installed. This warrant does not apply to uses not in compliance with specific applications and installation procedures. All warranty obligations of the manufacturer shall be limited, at the discretion of the manufacturer, to repair or replacement of the defective product. These remedies shall constitute the manufacturer's sole obligation and sole remedy of purchaser under this warranty. In no event will the manufacturer be responsible for incidental, consequential, or specific loss or damage however caused.

Concrete Sealers USA

P.O. Box 5464 | De Pere, WI 54115

Toll-Free: 888.583.2991 | Fax: 920.759.5100 | Emergency: 800.424.9300

info@concrete sealersusa.com | www.concrete sealersusa.com

CONCRETESEALERSUSA

Professional Concrete Solutions You Can Trust

Product Description

The CR302 is a high modulus thixotropic epoxy paste designed to seal cracks and adhere surface ports prior to the injection of our CR301 Injection Foam crack repair product. CR302 will cure in the presence of moisture although application onto wet surfaces is not recommended. It is ideal for do-it-yourselfers and inexperienced applicators or contractors due to its extended working time of 6-7 minutes. Allows for injection within 2-3 hours.

CAUTION

Consult Material Safety Data Sheet prior to use. Wear safety glasses and gloves. Avoid contact with skin and eyes.

USE ONLY AS DIRECTED

BATCH # 123456

EPOXY PASTE SURFACE SEALER

Epoxy Paste for Sealing Foundation Wall Cracks & Adhering Surface Ports Prior to Injection

PART B

Parts A and B are mixed
1:1 by volume.

FIRST AID

EYES: Flush with large amounts of water, minimum of 15 minutes. **SKIN:** Wash thoroughly with soap and water. Do not apply grease or ointments. **INHALATION:** Leave area for fresh air. **INGESTION:** Drink 3-4 glasses of water. Do not induce vomiting. Seek medical care immediately.

LIMITED WARRANTY – The Manufacturer warrants products to be free from defects in material or manufacturing. Products are further warranted for adequacy of design when used in accordance with design limits, and properly specified and installed. This warrant does not apply to uses not in compliance with specific applications and installation procedures. All warranty obligations of the manufacturer shall be limited, at the discretion of the manufacturer, to repair or replacement of the defective product. These remedies shall constitute the manufacturer's sole obligation and sole remedy of purchaser under this warranty. In no event will the manufacturer be responsible for incidental, consequential, or specific loss or damage however caused.

Concrete Sealers USA

P.O. Box 5464 | De Pere, WI 54115

Toll-Free: 888.583.2991 | Fax: 920.759.5100 | Emergency: 800.424.9300

info@concrete sealersusa.com | www.concrete sealersusa.com

CONCRETESEALERSUSA

Professional Concrete Solutions You Can Trust

Product Description

The CR302 is a high modulus thixotropic epoxy paste designed to seal cracks and adhere surface ports prior to the injection of our CR301 Injection Foam crack repair product. CR302 will cure in the presence of moisture although application onto wet surfaces is not recommended. It is ideal for do-it-yourselfers and inexperienced applicators or contractors due to its extended working time of 6-7 minutes. Allows for injection within 2-3 hours.

CAUTION

Consult Material Safety Data Sheet prior to use. Wear safety glasses and gloves. Avoid contact with skin and eyes.

USE ONLY AS DIRECTED

BATCH # 123456

EPOXY PASTE SURFACE SEALER

Epoxy Paste for Sealing Foundation Wall Cracks & Adhering Surface Ports Prior to Injection

PART A

Parts A and B are mixed
1:1 by volume.

FIRST AID

EYES: Flush with large amounts of water, minimum of 15 minutes. **SKIN:** Wash thoroughly with soap and water. Do not apply grease or ointments. **INHALATION:** Leave area for fresh air. **INGESTION:** Drink 3-4 glasses of water. Do not induce vomiting. Seek medical care immediately.

LIMITED WARRANTY – The Manufacturer warrants products to be free from defects in material or manufacturing. Products are further warranted for adequacy of design when used in accordance with design limits, and properly specified and installed. This warrant does not apply to uses not in compliance with specific applications and installation procedures. All warranty obligations of the manufacturer shall be limited, at the discretion of the manufacturer, to repair or replacement of the defective product. These remedies shall constitute the manufacturer's sole obligation and sole remedy of purchaser under this warranty. In no event will the manufacturer be responsible for incidental, consequential, or specific loss or damage however caused.

Concrete Sealers USA

P.O. Box 5464 | De Pere, WI 54115

Toll-Free: 888.583.2991 | Fax: 920.759.5100 | Emergency: 800.424.9300

info@concrete sealersusa.com | www.concrete sealersusa.com

CONCRETESEALERSUSA

Professional Concrete Solutions You Can Trust

Product Description

The CR302 is a high modulus thixotropic epoxy paste designed to seal cracks and adhere surface ports prior to the injection of our CR301 Injection Foam crack repair product. CR302 will cure in the presence of moisture although application onto wet surfaces is not recommended. It is ideal for do-it-yourselfers and inexperienced applicators or contractors due to its extended working time of 6-7 minutes. Allows for injection within 2-3 hours.

CAUTION

Consult Material Safety Data Sheet prior to use. Wear safety glasses and gloves. Avoid contact with skin and eyes.

USE ONLY AS DIRECTED

BATCH # 123456

EPOXY PASTE SURFACE SEALER

Epoxy Paste for Sealing Foundation Wall Cracks & Adhering Surface Ports Prior to Injection

PART B

Parts A and B are mixed
1:1 by volume.

FIRST AID

EYES: Flush with large amounts of water, minimum of 15 minutes. **SKIN:** Wash thoroughly with soap and water. Do not apply grease or ointments. **INHALATION:** Leave area for fresh air. **INGESTION:** Drink 3-4 glasses of water. Do not induce vomiting. Seek medical care immediately.

LIMITED WARRANTY – The Manufacturer warrants products to be free from defects in material or manufacturing. Products are further warranted for adequacy of design when used in accordance with design limits, and properly specified and installed. This warrant does not apply to uses not in compliance with specific applications and installation procedures. All warranty obligations of the manufacturer shall be limited, at the discretion of the manufacturer, to repair or replacement of the defective product. These remedies shall constitute the manufacturer's sole obligation and sole remedy of purchaser under this warranty. In no event will the manufacturer be responsible for incidental, consequential, or specific loss or damage however caused.

Concrete Sealers USA

P.O. Box 5464 | De Pere, WI 54115

Toll-Free: 888.583.2991 | Fax: 920.759.5100 | Emergency: 800.424.9300

info@concrete sealersusa.com | www.concrete sealersusa.com