

# **Technical Data Sheet (TDS)**

# **PS101 Siliconate Water Repellent WB Penetrating Sealer**

Zero VOC, Water Based Sealer for Concrete & Masonry

Page 1

## **Product Description**

PS101 is a chemically reactive deep penetrating siliconate sealer that is intended for unsealed and uncolored concrete. It creates a cross-linked insoluble methyl-silicone internal membrane that fuses within porous substrates of broom finished or smooth troweled concrete to combat freeze/thaw damage, reduce scaling and spalling, impart water repellence, and restrict moisture absorption. It also limits harmful effects of deicing chemicals and salts, acid rain deterioration, alkali attack, corrosion of reinforcing steel, and UV damage. PS101 decreases efflorescence, limits dirt buildup, retards mold and mildew, and makes easier to clean and maintain. PS101 is breathable with minimal impact to traction coefficient. It is also UV resistant and nonyellowing. PS101 has a clear appearance. Upon proper application, the substrate will have little, or no, noticeable change in appearance when dry.

## **Recommended Uses**

PS101 was originally developed for commercial and industrial applications and is widely used throughout North America to this day for those applications. Concrete Sealers USA is now also making this professional grade sealer available to the residential market so small contractors, applicators, and do-it-yourselfers can enjoy the same superior benefits that architects, engineers, and large contractors have enjoyed for years. PS101 is recommended for unsealed and uncolored broom finished or smooth troweled concrete and for sealing other cementitious and masonry surfaces such as stucco, block, mortar, and grout. It is ideal for sealing commercial and residential structures such as parking decks and structures, workshop floors, warehouse floors, pole barn and shed floors, basement floors, garage floors, driveways, sidewalks, walkways, porches, steps, pool decking, and patios. It is suitable for horizontal or vertical and interior or exterior applications. Not intended for below grade waterproofing.

### **Product Characteristics**

#### **SDS Information / Physical and Chemical Properties**

**Boiling Point:** 212° F

**Vapor Pressure:** 17.5 mmHg @ 20° C

Solubility in Water: Yes

**Evaporation Rate:** Similar to water

Appearance and Odor: Clear w/ Slightly Amine Odor

**Specific Gravity:**  $(H_20-1):1.1 \text{ to } 1.3 \otimes 20^{\circ}\text{C}$ 

% Volatile by Volume: 0 g/L

pH: 11.5 Flashpoint: N/A

Flammable Limits: Lower Limit: N/A; Upper Limit: N/A

Finish: Flat/Clear

**Drying Time\*\*:** Dry to touch 1-3 hours; traffic 6-12

hours

**Shelf Life\*\*\*:** 2 years unopened

**Coverage Rates\*:** 300-450 sq. ft./gal. for smooth troweled concrete and dense surfaces.

175-225 sq. ft./gal. for broom finished concrete surfaces.

100-150 sq. ft./gal. for concrete block.

<sup>\*</sup>Coverage rates are approximate and for estimating purposes only. Application rate based upon porosity and absorption. Always test absorption prior to application.

<sup>\*\*</sup>Drying times are for estimating purposes only. Actual drying time is based upon temperature, humidity, air flow.

<sup>\*\*\*</sup>Store container upright indoors in a cool, dry place and maintain temperature of 55°F to 85°F.

# **PS101 Siliconate Water Repellent WB Penetrating Sealer**

Zero VOC, Water Based Sealer for Concrete & Masonry

Page 2

#### **Performance Characteristics**

**ASTM D2939:** Resistance to water solubility, flexibility: No cracking

ASTM D466: Resistance to water flow and action: Excellent adhesion. No re-emulsification
ASTM E96: Water vapor transmission: .04 grains/sq/ft./hr. Water permeability: .102 perms

ASTM C836: Film thickness on a vertical scale: Passed SS-W-110C: Water repellence on masonry test: 1.925% ASTM C672: Scaling Resistance: Passed. No scaling

AASHTO 259 and T260: 90 Day Ponding: Passed
UV-Testing (Modified): No change. Excellent results
ASTM-Elcometer Pull (280 lbs): Concrete failed 1st. No delamination

**ASTM C642:** Absorption: Phase 1 (48 hrs): 0.62%; Phase 2 (50 days): 1.25%

NCHRP 244, Series IV (4.1 Southern Exposure): Absorbed chloride: <7% Absorbed chloride: <7% Absorbed chloride: <7% Absorbed chloride: <7% CHRP 244 Series (11 Cube Test: 3.1): <12% weight gain <9% absorbed chloride

Moisture Vapor Transmission Rate: 2%

#### Color

PS101 has a clear appearance. Upon proper application, the substrate will have little, or no, noticeable change in appearance when dry.

## **Ordering & Shipping Information**

Packaging: 1 gal. Jugs

5 gal. Pails 55 gal. Drums

**Shipping:** Normal package delivery and trucking

#### **Surface Preparation**

Substrates to be sealed ideally will be a minimum of 28 days old and/ or be fully cured. The surface must be porous enough to allow penetration into the substrate. If applied to freshly placed concrete, surfaces should be clean, dry, free of bleed water, final finishing process completed, and sufficient strength to be stood on without being marred. Added benefits can be obtained by waiting 7 days after placement when peak hydration and off gassing have slowed enough to allow better penetration of the sealer into the substrate. For existing surfaces, substrates should be clean and free of surface laitance, dust, dirt, debris, mildew, oil, grease, previous sealers, curing agents, paint or other surface coatings, and other contaminants. If acid or other cleaning compound is used for cleaning or etching the surface, neutralize the surface completely before application of PS101.

## **Application**

Always test porosity prior to application, especially on machine troweled concrete. Surface should be dry for proper penetration of the sealer. Should not apply to damp or wet surfaces or if rain is expected within 12 hours after application. Product is a one part system and requires no special mixing. Stir material thoroughly before and during application. Do not apply below 40°F or above 95°F during the application or drying period. Apply uniformly with a low pressure sprayer. When applying material, work in small, manageable areas at a time in order to maintain a wet edge. Product should be applied to the point of rejection and be fully absorbed within 10 minutes without puddles. Use a broom, roller, or microfiber pad to evenly distribute product as well as disperse any puddles as excessive application may result in white residue (especially on darker surfaces) which will not affect sealer performance and generally dissipates over time or by power washing. For dense surfaces, generally only one application is required. However, for extremely porous surfaces where additional product can be absorbed, a light secondary application may be able to be applied to enhance performance. Clean application materials with warm water.

# **PS101 Siliconate Water Repellent WB Penetrating Sealer**

Zero VOC, Water Based Sealer for Concrete & Masonry

Page 3

## **Limitations**

PS101 is designed to work only on porous concrete and masonry substrates and is not intended for asphalt. This product may damage vegetation or may etch glass, vinyl, aluminum, plastic, and metal. Avoid contact with eyes and skin. Sealer may be damaged if frozen prior to use. Not intended to seal cracks. Will not remediate structurally unsound surfaces with defects. PS101 is not oleophobic and is not intended as an oil repellent. The Company does not warranty specific performance results or compatibility with products manufactured by others. The Company shall bear no liability, other than replacement of defective product. A small test must be conducted prior to application. Based upon this test, the purchaser shall determine for themselves the suitability of this product for the intended use.

# **Environmental & Regulatory**

PS101 complies with EPA, FDA and OSHA strict requirements and contains no solvents or Volatile Organic Compounds (VOC). This product is considered a non-hazardous chemical under OSHA Hazard Communication Standard (29CFR 1910.1200). Contact may cause skin or eye irritation. Using with adequate air ventilation, eye protection, and gloves is recommended.

## **Safety & First Aid Precautions**

Flush with water for at least 15 minutes. Eyes: Skin: Wash thoroughly with soap and water.

Inhalation: Move subject to fresh air.

**Digestion:** Consult physician immediately.