

CONCRETE SEALERS *USA*

Professional Concrete Solutions You Can Trust

5 US Gallons

Product Description

PS102 is a chemically reactive deep penetrating silicate sealer that is intended for unsealed and uncolored rough concrete and masonry. It creates a cross-linked insoluble methyl-silicone internal membrane that fuses within porous substrates of broom finished concrete and concrete block to combat freeze/thaw damage, reduce scaling and spalling, impart water repellence, and restrict moisture absorption. It also limits harmful effects of deicing chemicals and salts, acid rain deterioration, alkali attack, corrosion of reinforcing steel, and UV damage. PS102 decreases efflorescence and dusting, limits dirt build up, retards mold and mildew, and makes easier to clean and maintain. PS102 is breathable with minimal impact to traction coefficient. PS102 also contains film forming polymers for enhanced curing of broom finished concrete by allowing the slow release of moisture during the curing process while maintaining excellent breathability. The film forming polymers also provide superior freeze/ thaw protection in harsh climates. It is also UV resistant and nonyellowing. PS102 has a light milky appearance. Upon proper application, the substrate will have little, or no, noticeable change in appearance when dry.

Recommended Uses

PS102 was originally developed for commercial and industrial applications and is widely used throughout North America to this day for those applications. Concrete Sealers USA is now also making this professional grade sealer available to the residential market so small contractors, applicators, and do-it-yourselfers can enjoy the same superior benefits that architects, engineers, and large contractors have enjoyed for years. PS102 is recommended for curing new broom finished concrete and for sealing existing unsealed and uncolored broom finished concrete and porous concrete block. It is ideal for sealing commercial and residential structures such as parking lots and structures, driveways, sidewalks, walkways, porches, steps, pool decking, patios, foundations, block walls, concrete pavers, and retaining walls. It is suitable for horizontal or vertical and interior or exterior applications. Not intended for below grade waterproofing.

Limitations

PS102 is designed to work only on porous concrete and masonry substrates and is not intended for asphalt. This product may damage vegetation or may etch glass, vinyl, aluminum, plastic, and metal. Avoid contact with eyes and skin. Sealer may be damaged if frozen prior to use. Not intended to seal cracks. Will not remediate structurally unsound surfaces with defects. PS102 is not oleophobic and is not intended as an oil repellent. The Company does not warrant specific performance results or compatibility with products manufactured by others. The Company shall bear no liability, other than replacement of defective product. A small test must be conducted prior to application. Based upon this test, the purchaser shall determine for themselves the suitability of this product for the intended use.

Environmental & Regulatory

PS102 complies with EPA, FDA and OSHA strict requirements and contains no solvents and only 8 g/L Volatile Organic Compounds (VOC). This product is considered a non-hazardous chemical under OSHA Hazard Communication Standard (29CFR 1910.1200). Contact may cause skin or eye irritation. Using with adequate air ventilation, eye protection, and gloves is recommended.

REFER TO SAFETY DATA SHEET PRIOR TO USE.

PS102 Silicate Water Repellent WB Penetrating Sealer

Low VOC, Water Based Sealer & Curing Agent for All Rough Concrete & Masonry

- Professional Grade
- One Step Application
- Dries Flat & Clear

- ▶ Combats Freeze/ Thaw
- ▶ Restricts Water & Moisture
- ▶ Limits Dirt Buildup
- ▶ Retards Mold & Mildew
- ▶ Resists Salts & Deicing Chemicals
- ▶ Decreases Efflorescence & Dusting
- ▶ Reduces Scaling & Spalling
- ▶ Makes Easier to Clean

Great for

**Driveways | Sidewalks | Walkways | Porches | Steps
Pool Decking | Patios | Foundations | Block Walls
Concrete Pavers | Retaining Walls**

Surface Preparation

The surface must be clean and porous enough to allow penetration into the substrate. Surfaces should be clean and free of surface laitance, dust, dirt, debris, mildew, oil, grease, previous sealers, curing agents, paint or other surface coatings, and other contaminants. If acid or other cleaning compound is used for cleaning or etching the surface, neutralize the surface completely before application of PS102.

Application

Always test porosity prior to application. Surface should be dry for proper penetration of the sealer. Should not apply to damp or wet surfaces or if rain is expected within 12 hours after application. Product is a one part system and requires no special mixing. Stir material thoroughly before and during application. Do not apply below 40°F or above 95°F during the application and drying period. Apply uniformly with a low pressure sprayer. When applying material, work in small, manageable areas at a time in order to maintain a wet edge. Product should be applied to the point of rejection and be fully absorbed within 10 minutes without puddles. Use a broom, roller, or brush to evenly distribute product as well as disperse any puddles as excessive application may result in white residue (especially on darker surfaces) which will not affect sealer performance and generally dissipates over time or by power washing. Generally, only one application is required. For curing new concrete, apply PS102 after all bleed water is gone, finishing is complete, and the concrete will withstand the weight of a person and not be marred. For new concrete where additional product can be absorbed, a light secondary application of PS102 may be able to be applied any time after 24 hours to enhance performance. Clean application materials with warm water.

Finish

Flat and clear.

Coverage Rate

200-300 sq. ft./Gal. for broom finished and rough surfaces. 150-200 sq. ft./Gal. for concrete block. Coverage rates are approximate and for estimating purposes only.

Drying Time

Dry to touch in 1-3 hours and for traffic in 6-12 hours. Drying times are for estimating purposes only. Actual drying times are based upon temperature, humidity, and air flow.

Shelf Life

2 years unopened.

Safety & First Aid Precautions

Eyes: Flush with water for at least 15 minutes. Skin: Wash thoroughly with soap and water. Inhalation: Move subject to fresh air. Digestion: Consult physician immediately.



Concrete Sealers USA

P.O. Box 5464 | De Pere, WI 54115

Toll-Free: 888.583.2991 | Fax: 920.759.5100 | Emergency: 800.424.9300

info@concretesealersusa.com | www.concretesealersusa.com

**Sustainable
GREEN
Product**

