

CONCRETE SEALERS *USA*

Professional Concrete Solutions You Can Trust

1 US Gallon

Product Description

PS112 is a state of the art residual free colloidal silica densifier concentrate designed to penetrate into most unsealed cementitious surfaces to densify, harden, and increase the strength of the top layer of a substrate while retaining its breathability. It is an electrostatically charged stable dispersion of 99.5% pure silica nanoparticles in an ultra low surface tension liquid solution. The low viscosity and 4-8 nm particle size allow it to penetrate deeply into a concrete surface and react rapidly and efficiently. The PS112 chemically reacts with calcium hydroxide within the matrix structure of concrete to form added Calcium Silicate Hydrate (CSH) which is the main binder in concrete. The PS112 also reacts with silica within the concrete surface as well as itself to further add density to the treated surface. It is easier and more efficient to apply than traditional sodium silicate densifiers, will not contribute to ASR (Alkali Silica Reaction), and will not leave behind stubborn mineral salt deposits with over application. It is an ideal treatment for machine troweled, burnished, or polished concrete surfaces. The PS112 improves the abrasion resistance and durability of a surface, provides long term protection against wear and traffic, reduces dusting not caused by actual surface defects, and lowers the overall maintenance of a surface. It is environmentally friendly, zero VOC, non-flammable, non yellowing, and odorless. PS112 has a clear appearance. Upon proper application, the substrate will have little, or no, noticeable change in appearance when dry. It can serve as a concrete polishing aid by producing better initial surface hardness that reduces polishing time and yields a smoother and denser burnished or polished surface. A polished appearance can normally be imparted to burnished or polished surfaces by applying with polishing pads and then buffing with a white pad. **1 gallon will yield 4 gallons when diluted 3:1 with clean water.**

Recommended Uses

PS112 is recommended as a densifier and hardener for machine troweled concrete surfaces. It can also be used on other cementitious surfaces where densifying and hardening benefits are desired. It can be used on low lime decorative concrete overlay products, integrally colored concrete, and is also compatible with most dyes and stains.

It is also recommended as a polishing aid for burnished or polished concrete surfaces. It is ideal for sealing commercial and residential concrete floors such as distribution center floors, factory floors, warehouse floors, automotive garage floors, retail store floors, pole barn and shed floors, workshop floors, basement floors, garage floors, and other machine troweled, burnished, or polished concrete surfaces. PS112 makes for an excellent primer as it does not interfere with the subsequent application of penetrating sealers, the bonding of topical coatings, or the adhesion of glues or mastics used in floor coverings.

Limitations

PS112 is designed to work only on porous concrete surfaces and is not intended for asphalt. This product may damage vegetation or may etch glass, vinyl, aluminum, plastic, and metal. Avoid contact with eyes and skin. Sealer may be damaged if frozen prior to use. Not intended to seal cracks. Will not remediate structurally unsound surfaces with defects such as chronic dusting or chalking. The use of high alkaline or acidic cleaners on the treated surface is not recommended and can be damaging. The Company does not warrant specific performance results or compatibility with products manufactured by others. The Company shall bear no liability, other than replacement of defective product. A small test must be conducted prior to application. Based upon this test, the purchaser shall determine for themselves the suitability of this product for the intended use.

Environmental & Regulatory

PS112 complies with EPA, FDA and OSHA strict requirements and contains no solvents or Volatile Organic Compounds (VOC). This product is considered a non-hazardous chemical under OSHA Hazard Communication Standard (29CFR 1910.1200). Contact may cause skin or eye irritation. Using with adequate air ventilation, eye protection, and gloves is recommended.

REFER TO SAFETY DATA SHEET PRIOR TO USE.

PS112 Colloidal Silica Densifier WB Penetrating Sealer

Zero VOC, Water Based Concrete Floor Densifier & Hardener Concentrate (Makes 4 Gallons)

- Professional Grade
- Dries Flat & Clear
- Dilute 3:1 with Clean Water

- ▶ Densifies & Hardens
- ▶ Protects Against Wear
- ▶ Lowers Maintenance
- ▶ Maintains Traction
- ▶ Decreases Dusting
- ▶ Increases Surface Strength
- ▶ Enhances Abrasion Resistance
- ▶ Acts as a Polishing Aid

Great for

Workshop Floors | Warehouse Floors | Automotive Garage Floors
Retail Store Floors | Pole Barn & Shed Floors | Basement Floors
Garage Floors

Surface Preparation

Substrates to be sealed ideally will be a minimum of 28 days old and/ or be fully cured. For freshly placed concrete, surfaces should be clean, dry, free of bleed water, final finishing process completed, and porous enough to allow penetration into the substrate. Added benefits can be obtained by waiting 3-7 days after placement when peak hydration and off gassing have slowed enough to allow better penetration of the sealer into the substrate. For existing surfaces, substrates should be clean and free of surface laitance, dust, dirt, debris, mildew, oil, grease, previous sealers, curing agents, paint or other surface coatings, and other contaminants. If acid or other cleaning compound is used for cleaning or etching the surface, neutralize the surface completely before application of PS112.

Application

Always test porosity prior to application, especially on very dense surfaces. Surface should be dry for proper penetration of the sealer. Should not apply to damp or wet surfaces. **Product is concentrated and should be mixed 3 parts of clean water to 1 part of product.** Shake product first before mixing with water. When mixing with water, stir material thoroughly before and during application. Do not apply below 40°F or above 95°F during the application or drying period. Apply uniformly with a low pressure sprayer. When applying material, work in small, manageable areas at a time in order to maintain a wet edge. Product should be applied to the point of rejection and be fully absorbed within 20 minutes without puddles. Use a broom, roller, or microfiber pad to evenly distribute product as well as disperse any puddles as excessive application may result in a dry powdery substance on the surface once dry. This residual material will not affect sealer performance and generally can be rinsed away with water or swept away 2 hours after final application of sealer. Generally, only one application is required. If additional coats are desired and more product can be absorbed, wait approximately 1-2 hours between coats. For a more polished appearance on burnished or polished surfaces, apply using polishing pads and then buffing with a white pad. Clean application materials with warm water.

Generally, only one application is required. If additional coats are desired and more product can be absorbed, wait approximately 1-2 hours between coats. For a more polished appearance on burnished or polished surfaces, apply using polishing pads and then buffing with a white pad. Clean application materials with warm water.

Finish

Under normal conditions, the sealer will dry clear and flat. However, a polished appearance can normally be imparted to burnished or polished concrete surfaces by applying with polishing pads and then buffing with a white pad. Polished appearance is based solely upon application procedure of the applicator.

Coverage Rate

300-450 sq. ft./Gal. for machine troweled and smooth surfaces and 400-600sq. ft./Gal. for polished surfaces. Coverage rates are approximate and for estimating purposes only.

Drying Time

Dry for traffic in 1-2 hours. Drying times are for estimating purposes only. Actual drying times are based upon temperature, humidity, and air flow.

Shelf Life

1 year unopened.

Safety & First Aid Precautions

Eyes: Flush with water for at least 15 minutes. Skin: Wash thoroughly with soap and water. Inhalation: Move subject to fresh air. Digestion: Consult physician immediately.



MADE IN THE USA

Concrete Sealers USA

P.O. Box 5464 | De Pere, WI 54115

Toll-Free: 888.583.2991 | Fax: 920.759.5100 | Emergency: 800.424.9300

info@concretesealersusa.com | www.concretesealersusa.com

Sustainable
GREEN
Product

